



Module	2
Helical Angle	19°31' 42''
Angle	Right-Hand
Teeth No.	150
Pressure Angle	20°
Material	C45E
Heat treatment	Induction Hardened
Hardness	HRC 50-55
Sides Surfaces Treatment	Ground
Teeth Surfaces Treatment	Ground
Surfaces Treatment	Ground
Quality Grade	DIN 6

**NATECH** HHG0210-6  
MADE IN TAIWAN

Quality Class :  
Tooth Thickness : -0.036mm  
Single Pitch Error : ±0.008mm  
Total Pitch Error : ±0.035mm

Date : 23.APR.2021		
Drawing Code: HHG0210-6		
Weight: 4.2 KG		Rev. A