



Module	2
Helical Angle	19°31' 42''
Angle	Right-Hand
Teeth No.	300
Pressure Angle	20°
Material	C45E
Heat treatment	Induction Hardened
Hardness	HRC 50°-55°
Sides Surfaces Treatment	Ground
Teeth Surfaces Treatment	Ground
Surfaces Treatment	Ground
Quality Grade	DIN 6

NATECH HHG0220-6
MADE IN TAIWAN

Quality Class :

Tooth Thickness : -0.036mm
Single Pitch Error : ±0.008mm
Total Pitch Error : ±0.035mm

Date : 24.SEP.2021		
Drawing Code: HHG0220-6		
Weight: 8.2 KG		Rev. A